

RESISTENCIA A LA TRACCION INDIRECTA A LOS 28 DIAS							
CURADO	A/C	0% AR	10%AR	20%AR	30% AR	30% AR + 5% MS	30% AR + 10% MS
	0,65C		2,82	2,66	3,37	2,55	3,57
NO CURADO	A/C	0% AR	10%AR	20%AR	30% AR	30% AR + 5% MS	30% AR + 10% MS
	0,65 NC		1,91	1,96	3,02	2,43	3,27

A/C	MAX	MIN	0% AR	10%AR	20%AR	30% AR	30% AR + 5% MS	30% AR + 10% MS
0,65	32%	5%	32%	26%	10%	5%	8%	8%

